

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representation of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

## **IMAGES ARE BEST AVAILABLE COPY**

**As rescanning documents *will not* correct images, please do not report the images to the Image Problem Mailbox.**

22 8556

# NO DRAWINGS

Priority Date(s):	18.4.88
Complete Specification Filed:	31.3.89
Class:	C.08L23/08, 18
Publication Date:	26 OCT 1990
P.O. Journal, No:	1337

Patents Form No. 5

PATENTS ACT 1953

COMPLETE SPECIFICATION

CROSSLINKED POLYMER COMPOSITIONS, A PROCESS FOR THEIR  
PRODUCTION AND MOULDED ARTICLES OBTAINED

WE, NORSOLOR, a French company of Tour Aurore, Places des Reflets, F-92080 Paris La Defense - Cedex 5, France, hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:-

-1-

(Followed by 1a)



5 The present invention relates to a polymer composition based on at least one propylene polymer mixed with at least one flexible ethylene copolymer, the ratio by weight of the propylene polymer(s) to the flexible ethylene copolymer(s) being in the range 15:85 to 50:50. The present invention also relates to a production process for this composition and to the moulded articles obtained from the latter.

10 "Flexible ethylene copolymers" is understood to mean essentially terpolymers of ethylene, alkyl (meth)acrylate and unsaturated dicarboxylic anhydride, containing more than 85 mol% of ethylene, and having a flexural modulus of elasticity less than 100 MPa and, preferably, less than 30 MPa.

15 The polymer compositions, also occasionally designated below by the term "alloys", comprising the mixtures of polypropylene with the terpolymers mentioned above are known from the European Patent No. 0,221,919. These alloys have the following disadvantage: when the terpolymer content exceeds 50% by weight, their morphology develops towards interpenetrating phases, then towards a morphology having a terpolymer matrix and polypropylene nodules. Now, in the domain of the interpenetrating phases, the morphologies are sensitive to shearing gradients which can be applied in later use, and the mechanical properties of the alloy are generally poor and hardly reproducible.

25 Additionally, crosslinked polymers of ethylene and an unsaturated dicarboxylic anhydride, optionally with another comonomer, are known particularly from the French Patent No. 2,131,540 and from the patent US-A-4,612,349.

30 The Applicant Company has now confirmed that when terpolymers of the type defined above are subjected to at least partial chemical crosslinking during the production of alloys with propylene polymers, meaning during the kneading of the two polymer constituents, polymer com-

positions are obtained from which the defects mentioned above are eliminated. This method of crosslinking is designated in what follows as being a "dynamic crosslinking".

5           The polymer compositions which result are characterized by a non-progressive morphology during later use by injection or extrusion and are characterized by improved mechanical properties. They are also distinguished by having an improved thermal behaviour, characterized by the increase in the Vicat softening temperature, or by the increase in the torsion modulus of elasticity. Their elastic memory is improved and is manifest in a lower compression set (generally between about 55% and 80% in accordance with the standard ASTM D395 after 22 hours at 70°C).

10           Moreover, these polymer compositions are distinguished from those described in the European Patent Application No. 204,453, in which the flexible ethylene copolymer is also subjected to a dynamic crosslinking, among other differences, by the replacement of the acrylic acid by an unsaturated dicarboxylic anhydride, which has the advantage of promoting an improved compatibility between the propylene polymer and the flexible ethylene copolymer.

20           The present invention relates to a polymer composition based on a mixture of :

- about 15 to 50% by weight of a propylene polymer; and
- about 50 to 85% by weight of a flexible ethylene copolymer,

30           characterized by the fact that the said flexible ethylene copolymer is a terpolymer (A) comprising:

- from about 83 to 92.7 mol% of ethylene,
- from about 7 to 14 mol% of at least one alkyl acrylate, whose alkyl group has from 1 to 8 carbon atoms; and
- from about 0.3 to 3 mol% of at least one unsaturated dicarboxylic anhydride; or else

35           a mixture comprising, for 100 parts by weight, at least

about 70 parts by weight of the terpolymer (A) and at most about 30 parts by weight of at least one copolymer (B) selected from ethylene copolymers comprising:

- from about 86 to 93 mol% of ethylene; and
- from about 7 to 14 mol% of at least one copolymerizable monomer selected from alkyl (meth)acrylates whose alkyl group has from 1 to 8 carbon atoms; and ethylene copolymers comprising:

- about 92 to 98 mol% of ethylene; and
- from about 2 to 8 mol% of at least one C<sub>3</sub>-C<sub>10</sub>  $\alpha$ -olefin,

the said ethylene/ $\alpha$ -olefin copolymers having a density in the range of about 0.875 to 0.905,

the terpolymer (A) having undergone at least a partial dynamic crosslinking, using a crosslinking agent containing at least one functional group capable of reacting with the anhydride functional group of the said terpolymer (A).

Preferably, the molar ratio of the reactive functional groups of the crosslinking agent to the anhydride groups of the terpolymer (A) is between 0.5 and 2.

The propylene polymers which may be used according to the present invention comprise particularly crystalline polypropylene, crystalline ethylene-propylene block copolymers or crystalline ethylene-propylene random copolymers, crystalline propylene- $\alpha$ -olefin copolymers, the olefin having from 4 to 10 carbon atoms, and mixtures of these polymers. These normally have a melt flow index lying between 0.5 and 20 dg/min., measured in accordance with the standard ASTM D1238, at 230°C, under 2.16 kg.


As alkyl acrylates from which polymers (A) and (B) may be constituted, may be mentioned particularly n-butyl acrylate, ethyl acrylate, 2-ethylhexyl acrylate and isobutyl acrylate.

As unsaturated dicarboxylic anhydrides from which the terpolymers (A) are constituted, may be mentioned maleic anhydride, itaconic anhydride and phthalic anhydride, more particularly, maleic anhydride.

- 4 -

In accordance with a first embodiment of the invention, the crosslinking agent contains at least one epoxide group.

The crosslinking agent may thus be a polyepoxide compound of the general formula:



in which A is a polyfunctional group of valence n,  $n \geq 2$  and R is a hydrocarbon radical or a hydrogen atom. Polyglycidyl ethers of polyhydroxyl-substituted compounds may be mentioned by way of examples. Among these, are chosen either polyepoxide compounds of the aromatic type (such as those derived from Bisphenol A), or polyepoxide compounds of the aliphatic type, particularly polyglycidyl ethers of polyalcohols, such as diglycidyl ethers of  $\alpha$ - $\omega$  diols such as the diglycidyl ether of butanediol, of hexanediol, of paracyclohexyldimethanol, of neopentyl glycol, such as the triglycidyl ethers of triols such as trimethylolpropane triglycidyl ether, glycerol triglycidyl ether, such as the tetraglycidyl ethers of tetrols such as pentaerythritol tetraglycidyl ether. Among compounds originating from the epoxidation of olefinic compounds, epoxidized soya oil is advantageously selected.

It is also possible to use, as the crosslinking agent having epoxy functional groups, a copolymer of at least one  $C_2-C_8$  olefin with at least one unsaturated monomer containing an epoxy group, such as particularly a glycidyl acrylate or a glycidyl methacrylate. A copolymer of this type can be obtained, either by grafting an unsaturated monomer onto the chain of the olefin (co)-polymer or directly by copolymerization of the unsaturated monomer with the  $C_2-C_8$  olefin. A copolymer of this type may additionally comprise units derived from another unsaturated monomer such as an alkyl acrylate or an alkyl methacrylate. Such copolymers have been described



particularly in the Patent US-A-3,383,372.

5 The epoxide crosslinking agents are advantageously combined with at least one activator of the reaction between their epoxide functional groups and the anhydride functional groups of the terpolymer (A). Such  
10 activators are well known and comprise for example tertiary amines, quaternary ammonium salts, triphenylphosphine, zinc alkyldithiocarbamates and methylimidazole. The molar ratio of the activating agent to the anhydride groups of the terpolymer (A) is generally at least equal to 0.5, preferably at least equal to 1.

15 As a particular epoxide crosslinking system, may be mentioned bisphenol A diglycidyl ether combined with a mixture of tertiary amines having 16 to 18 carbon atoms, known by the name of dimethylsuifamine. (sic).

20 In accordance with a second embodiment of the invention, the crosslinking agent contains at least two primary and/or secondary amine groups, preferably primary amine groups. By way of examples of such compounds, may be mentioned hexamethylenediamine, polyoxyethylenediamines, polyoxypropylenediamines, polyoxypropylenetriamines and diphenylsulfonodiamine. Polyamides having free amine functional groups may also be mentioned.

25 Polyamides which can be used are particularly polyamides obtained from (a) 35 to 49.5 mol% of dimeric fatty acid, (b) 0.5 to 15 mol% of monomeric fatty acid having a chain length of 12 to 22 carbon atoms, and (c) 2 to 35 mol% of polyetheramine of the general formula:  
30  $H_2N-R_1-O-(RO)_x-R_2-NH_2$  in which x represents a number between 8 and 80, particularly between 8 and 40;  $R_1$  and  $R_2$  represent aliphatic and/or cycloaliphatic hydrocarbon radicals, which may be identical or different; and R represents an aliphatic hydrocarbon radical which may be branched, having 1 to 6 carbon atoms, and (d) 15 to 48  
35 mol% of aliphatic diamine containing 2 to 40 carbon atoms in the carbon skeleton, it being possible to replace the dimeric fatty acids to the extent of 2/3 by aliphatic dicarboxylic acids having 4 to 12 carbon atoms; and polyamides obtained from (a) 20 to 49.5 mol% of dimeric

5 fatty acids, (b) 0.5 to 15 mol% of monomeric fatty acids having a chain length of 12 to 22 carbon atoms; and (c) up to 20 to 55 mol% of an amine having at least two primary amino groups and having 2 to 40 carbon atoms in the carbon skeleton, it being possible to replace the dimeric fatty acids to the extent of 2/3 by aliphatic dicarboxylic acids having 4 to 12 carbon atoms. These polyamides advantageously have terminal amino groups, their amine number being in the range 2 to 15, particularly 4 to 10.

10 In accordance with a third embodiment of the present invention, the crosslinking agent contains at least two alcohol or thiol functional groups. In particular, may be mentioned diols, such as ethylene glycol, propylene glycol and their polymers. The crosslinking agent may also simultaneously contain at least one alcohol or thiol functional group and at least one amine functional group. Diethanolamine and monoethanolamine may be mentioned as crosslinking agents of this type.

15 20 The compositions according to the invention generally have a content of materials which are extractable at 23°C by cyclohexane, this content revealing their degree of crosslinking, and being between about 80% and 100%.

25 30 35 The composition according to the invention may contain up to about 20 parts by weight, per 100 parts by weight of total polymers, of at least one inorganic filler, selected particularly from mica, carbon black, chalk, talc and kaolin. It may also contain up to about 30 parts by weight, per 100 parts by weight of total polymers, of at least one plasticizing oil which is compatible with the ethylene copolymer. Among these plasticizers, may be mentioned paraffin oils and isoparaffin oils, naphthenic oils, aromatic oils and alkyl phthalates.

The production of polymer compositions of the invention is carried out by kneading the polymer constituents, the crosslinking agent and optional additives, in internal mixers or continuous kneaders having twin



5 screws or co-kneaders, at a temperature generally of  
between 190 and 240°C, the residence time in the kneading  
apparatus being generally more than 2 minutes. The  
crosslinking agent may be introduced in the kneader by  
10 different known techniques. When the crosslinking agent  
is liquid, it may be introduced directly by pumping into  
the kneading apparatus or else a master-batch may be  
formed by dispersing this agent in the copolymer (B) in  
the case where such a copolymer is present; in the case  
15 where the crosslinking agent is a particulate material,  
it is possible to produce a coating of the polymer  
granules with a mixture of the said crosslinking agent  
and a particulate filler, such as chalk under cold  
conditions.

20 Finally, the invention also relates to moulded  
objects obtained from a composition of the type pre-  
viously described, by a conversion technique, by injec-  
tion moulding, extrusion, etc. Articles of this kind find  
particularly valuable application in the following areas:

25 The present invention will now be described in  
more detail with reference to examples and comparative  
examples. In the latter, the percentages are given by  
weight unless stated otherwise.

- The melt flow indices of the propylene polymers  
25 have been calculated in accordance with the standard ASTM  
D1238, at the temperature indicated, under 2.16 kg.

- The measurements of tensile strength and elonga-  
30 tion at break were carried out in accordance with the  
standard ASTM D638: starting from a granular mixture  
obtained after kneading, 2 mm thick plaques are produced  
by injection moulding at a resin temperature of 220°C,  
from which tensile test pieces are cut; here, distinction  
is made between the cut in the injection direction (L)

and the cut perpendicular to the injection direction (T).

- The measurements of compression set were carried out in accordance with the standard ASTM D 395 after 22 hours at 70°C.

5 - The measurements of Vicat softening temperature were carried out in accordance with the standard ASTM D1525.

- The torsion modulus of elasticity at 100° was calculated in accordance with the standard ISO 150,527.

10 - The crosslinking of the terpolymers (A) of the invention was revealed by extraction of the alloy with cyclohexane at 23°C for 48 hours, followed by measurement of the content of extractable materials (gel) by evaporation of the solvent.

15 The results of the measurements carried out in Examples 1 to 5 and in the corresponding Comparative Examples are shown in Table 1.

Comparative Example 1

20 In a BUSS PR 46 co-kneader are continuously mixed, at a temperature of 205°C, a propylene homopolymer having a melt flow index (MFI) of 4 g/10 minutes (at 230°C), and a terpolymer comprising:

- 90.3 mol% of ethylene;
- 9.0 mol% of butyl acrylate, and
- 25 - 0.7 mol% maleic anhydride,

this terpolymer having an MFI of 9.5 g/10 minutes (190°C), a fusion temperature of 67°C and a crystallinity less than 5%, the ratio by weight polypropylene/terpolymer being 50/50. This mixture is recovered in the form of granules.

30 Example 1

The procedure of Comparative Example 1 is followed, except that 1% of diethanolamine relative to the terpolymer is incorporated in the polypropylene/terpolymer mixture.

35 Comparative Example 2

The procedure of Comparative Example 1 is followed, except that the terpolymer is a terpolymer comprising:

- 89.4 mol% of ethylene;
  - 9.2 mol% of ethyl acrylate; and
  - 1.2 mol% of maleic anhydride,
- and having an MFI of 33.2 g/10 minutes (at 190°C), and a fusion temperature of 70°C.

Example 2

The procedure of Comparative Example 2 is followed, except that 1% of diethanolamine relative to the terpolymer is incorporated in the polypropylene/terpolymer mixture.

Comparative Example 3

The procedure of Comparative Example 2 is followed, except that the ratio by weight polypropylene/terpolymer is 30/70.

Example 3

The procedure of Comparative Example 3 is followed, except that 1% of diethanolamine relative to the terpolymer is incorporated in the mixture.

Comparative Example 4

In a BUSS PR 46 mixer, are mixed, at a temperature of 205°C, 50 parts of a random propylene copolymer, having a fusion temperature of between 150 and 158°C and an MFI of 10-15 g/10 minutes (at 230°C), and 50 parts of the terpolymer defined in Comparative Example 2.

Example 4

The procedure of Comparative Example 4 is followed except that the 50 parts of terpolymer are replaced by a mixture of:

- 40 parts by weight of the terpolymer defined in Comparative Example 2; and
- 10 parts by weight of the copolymer comprising:
  - 91.4 mol% of ethylene; and
  - 8.6 mol% of n-butyl acrylate,

into which mixture are incorporated 4 parts by weight of diethanolamine per 100 parts by weight of the copolymer previously mentioned.

Comparative Example 5

The procedure of Comparative Example 4 is followed except that the ratio by weight of the polypropy-

22 8536

lene/terpolymer mixture is 30/70.

Example 5

The procedure of Example 4 is followed except that the ratio by weight of the mixture polypropylene/terpolymer/copolymer is 30/56/14.

5

Table 1

	Comp.	Ex. 1	Comp.	Ex. 2	Comp.	Ex. 3	Comp.	Ex. 4	Comp.	Ex. 5
	Ex. 1		Ex. 2		Ex. 3		Ex. 4		Ex. 5	
Tensile strength (in MPa)										
L	14.4	18.3	14.8	20.0	10.2	14.2	13.0	16.9	9.9	12.5
T	11.4	18.4	10.7	16.4	5.9	10.4	9.3	20.6	10.2	15.1
Elongation (%)										
L	96	184	68	246	94	162	125	341	220	241
T	379	426	107	295	52	187	160	684		
Vicat softening temperature (°C)										
	72	97	60	104	42	62	68	81	52	62
Shore hardness										
			50D	52D	81A	85A	75A	80A	72A	79A
Calorimetric content (%)										
							65	96		



228SS6

Comparative Example 6

In a BUSS kneader, are mixed, at a temperature of 205°C, the polypropylene of Example 4 and the ethylene-ethyl acrylate-maleic anhydride terpolymer of Example 1.

The results of the measurements carried out are shown in Table 2.

Example 6

The procedure of Comparative Example 6 is followed, except that to the mixture based on the polypropylene of Example 4 and on the terpolymer of Example 1 are added:

- 3% of bisphenol A diglycidyl ether (molecular weight 340) relative to the terpolymer; and
- 3% of dimethylsuifamine (sic) relative to the terpolymer.

The results of the measurements carried out are shown in Table 2.

Table 2

	Comp. Ex. 6	Ex. 6
Compression set (70°C, 22 hours)	100	77
Tensile strength (L) (MPa)	13	17
Gel content (%)	70	97

The results of the measurements carried out in Examples 7 to 10 and in the corresponding Comparative Examples are shown in Table 3.

Comparative Example 7

The process of Comparative Example 1 is followed, except that the ratio by weight polypropylene/terpolymer is 40/60.

Example 7

The procedure of Comparative Example 7 is followed, except that a polypropylene/terpolymer/diethanol-

amine mixture is used in a ratio by weight of 39/60/1.

Comparative Example 8

The procedure of Comparative Example 1 is followed, except that the ratio by weight polypropylene/terpolymer is 20/80.

Example 8

The procedure of Comparative Example 8 is followed, except that a polypropylene/terpolymer/copolymer of Example 4/diethanolamine mixture is used in ratio by weight of 20/64/15.35/0.65.

Comparative Example 9

The procedure of Comparative Example 1 is followed, except that as propylene polymer, a homopolymer having an MFI of 12 dg/min (230°C) and a fusion point of 168°C is used, the ratio by weight polypropylene/terpolymer being 40/60.

Example 9

The procedure of Comparative Example 9 is followed, except that the mixture having the following formulation is used:

Polypropylene from Comp. Ex. 9 .....	40 (% by weight)
Terpolymer from Comp. Ex. 9 .....	42
Linear ethylene-propylene-butene copolymer of density 0.900 g/cm <sup>3</sup> , of MFI 1.1 dg/min (190°C) .....	12
Chalk .....	3.6
Epoxy resin .....	2.1
Dimethylsulfamine (sic) .....	0.3

Comparative Example 10


The procedure of Comparative Example 9 is followed, except that the ratio by weight polypropylene/terpolymer is 30/70.

Example 10

The procedure of Example 9 is followed, except that the percentages by weight of the constituents of the mixture, taken in the same order, are as follows:  
30;50;14;4.2;3.5;0.3.

Table 3

	Comp. Ex. 7	Ex. 7	Comp. Ex. 8	Ex. 8	Comp. Ex. 9	Ex. 9	Comp. Ex. 10	Ex. 10
Tensile strength (in MPa)								
L	11.0	18.6	8.2	12.5	15.9	16.1	10.4	15.8
T	11.2	15.4	6.4	10.5	12.7	12.5	10.3	13.3
Elongation at break (%)								
L	180	489	315	448	80	244	157	340
T					83	267		
Compression set (22 hours, 70°C) (%)								
	100	70	100	65	100	59	100	59
Torsion modulus at 100° (in MPa)								
	0.2	15	<0.1	3				
Shore A hardness								
	86	89		82		98		96
Gel content								
	60	92						



228556



The results of the measurements carried out in Examples 11 and 12 and in the corresponding comparative examples are shown in Table 4.

Comparative Example 11

The procedure of Comparative Example 1 is followed, except that the polypropylene of Example 4 is used.

Example 11

The procedure of Comparative Example 11 is followed, except that a mixture is used having the following formulation:

Polypropylene from Comp. Ex. 11 ...	50 (% by weight)
Terpolymer from Comp. Ex. 11 .....	40
Ethylene/ethyl acrylate/glycidyl methacrylate (molar composition 96/2/2), having an MFI of 8 dg/min (at 190°C).....	10
Dimethylsulfamine (sic) .....	0.75

Comparative Example 12

The procedure of Comparative Example 11 is followed, except that the ratio by weight polypropylene/terpolymer is 30/70.

Example 12

The procedure of Example 11 is followed, except that the percentage by weight of the constituents of the mixture, taken in the same order, are the following: 30;56;14;1.0.

Table 4

	Comp. Ex. 11	Ex. 11	Comp. Ex. 12	Ex. 12
Vicat softening temperature (°C)	68	97	52	60
Compression set (22 hours, 70°C) (%)	100	75	100	65

22 8556

CLAIM 1

1. Polymer composition based on a mixture of :

- 15 to 50% by weight of a propylene polymer;
- and
- 50 to 85% by weight of a flexible ethylene copolymer,

characterized by the fact that the said flexible ethylene copolymer is a terpolymer (A) comprising:

- from 83 to 92.7 mol% of ethylene,
- from 7 to 14 mol% of at least one alkyl (meth)acrylate, whose alkyl group has from 1 to 8 carbon atoms; and
- from 0.3 to 3 mol% of at least one unsaturated dicarboxylic anhydride; or else

a mixture comprising, for 100 parts by weight, at least 70 parts by weight of the terpolymer (A) and at most 30 parts by weight of at least one copolymer (B) selected from ethylene copolymers comprising:

- from 86 to 93 mol% of ethylene; and
- from 7 to 14 mol% of at least one copolymerizable monomer selected from alkyl (meth)acrylates whose alkyl group has from 1 to 8 carbon atoms; and

ethylene copolymers comprising:

- 92 to 98 mol% of ethylene; and
  - from 2 to 8 mol% of at least one C<sub>3</sub>-C<sub>10</sub>  $\alpha$ -olefin,
- the said ethylene/ $\alpha$ -olefin copolymers having a density in the range of 0.875 to 0.905,

the said terpolymer (A) having undergone at least a partial dynamic crosslinking, using a crosslinking agent containing at least one functional group capable of reacting with the anhydride functional group of the said terpolymer (A).

2. Polymer composition according to Claim 1, characterized by the fact that the molar ratio of the reactive functional groups of the crosslinking agent to the anhydride groups of the terpolymer (A) is between 0.5 and 2.

3. Polymer composition according to one of Claims 1 and 2, characterized by the fact that the propylene


- 17 -

polymer is a polymer which has a melt flow index lying between 0.5 to 20 dg/min, measured in accordance with the standard ASTM D1283, at 230°C, under 2.16 kg.

4. Polymer composition according to one of Claims 1 to 3, characterized by the fact that the unsaturated dicarboxylic anhydride from which the terpolymers (A) are constituted is selected from maleic anhydride, itaconic anhydride and phthalic anhydride.

5. Polymer composition according to one of Claims 1 to 4, characterized by the fact that the crosslinking agent contains at least one epoxide functional group.

6. Composition according to Claim 5, characterized by the fact that the crosslinking agent is selected from polyepoxide compounds of the general formula:



O

in which A is a polyfunctional group of valence  $n$ ,  $n \geq 2$  and R is a hydrocarbon radical or a hydrogen atom, and copolymers of at least one  $C_2-C_6$  olefin with at least one unsaturated monomer containing an epoxy group.

7. Composition according to one of Claims 5 and 6, characterized by the fact that the epoxide crosslinking agent is combined with at least one activator of the reaction between its epoxide functional groups and the anhydride functional groups of the terpolymer (A), the molar ratio of the said activating agent to the anhydride groups of the terpolymer (A) being at least equal to 0.5.

8. Composition according to one of Claims 1 to 4, characterized by the fact that the crosslinking agent contains at least two primary and/or secondary amine functional groups.

9. Composition according to Claim 8, characterized by the fact that the crosslinking agent is selected from hexamethylenediamine, polyoxyethylenediamines, polyoxypropylenediamines, polyoxypropylenetriamines, diphenylsulphonediamine, and polyamides having free amine functional groups.



- 18 -

10. Composition according to one of Claims 1 to 4, characterized by the fact that the crosslinking agent contains at least two alcohol or thiol functional groups or else at least one alcohol or thiol functional group and at least one amine functional group.
11. Composition according to one of Claims 1 to 10, characterized by the fact that it contains up to 20 parts by weight, per 100 parts by weight of the total polymers, or at least one filler.
12. Composition according to one of Claims 1 to 11, characterized by the fact that it contains up to 30 parts by weight, per 100 parts by weight of the total polymers, of at least one plasticizing oil which is compatible with the ethylene copolymer.
13. Process for the production of the polymer composition, as defined in one of Claims 1 to 12, characterized by the fact that kneading of the polymer constituents, the crosslinking agent and optional additives is carried out at a temperature of between 190°C and 240°C, the residence time in the kneading apparatus being more than 2 minutes.
14. Moulded articles obtained from the polymer composition as defined in one of Claims 1 to 12.
15. A polymer composition as claimed in any one of claims 1-12, substantially as hereinbefore described and with reference to any one of the Examples.



NO COLOR

by their authorized agents

P.L. BERRY &amp; ASSOCIATES

per: *BZ*

**Intellectual Property Details**

Patent Number	228556
International Application Number	
WO Publication Number	
Patent Type	Patent Convention
Current Status	Granted and Sealed
Patent Title	CROSSLINKED POLYMER COMPOSITIONS, A PROCESS FOR THEIR PRODUCTION AND MOULDED ARTICLES OBTAINED

**Documents**

Abstract/Abridgement	<u>Document</u>
----------------------	-----------------

**Class**

Classification	Schedule and Edition
IPC C08L23/00	IPC2

**Dates**

Filed Date	31-03-1989
Renewal Date	31-03-2002

**Conventions**

Number	Date	Country
	18-04-1988	France

**Associations**

No associations on record or public access is restricted

**Actions**

Date	Action
26-11-1996	Registered
31-03-1996	Renew
25-03-1996	Renew
31-03-1993	Renew
31-03-1989	Filed

**Applicants & Licensees**

Applicant:	NORSOLOR
Address	Address not held

**Applicant & Licensee History**

No applicants nor licensees on record or public access is restricted

**Inventors**

No inventors on record or public access is restricted

- (11) 228556. (22) 31 Mar 1989.  
 (54) POLYMER COMPOSITION COMPRISED OF A FLEXIBLE  
 ETHYLENE COPOLYMER AND A PROPYLENE POLYMER.  
 (51) C08L23/08, 10.  
 (71) Norsoy.  
 (72) Hert, Marius.  
 (31) 88 8805066; (32) 18 Apr 1988; (33) FR.  
 (74) PLB

(57) This polymer composition is based on a mixture of: 15 to 50% by weight of a propylene polymer; and 50 to 85% by weight of a flexible ethylene copolymer, characterised by the fact that the flexible ethylene copolymer is a terpolymer (A) comprising of: from 83 to 92.7 mol% of ethylene, from 7 to 14 mol% of at least one alkyl (meth)acrylate, whose alkyl group has from 1 to 8 carbon atoms; and from 0.3 to 3 mol% of at least one unsaturated dicarboxylic anhydride; or else a mixture comprising of, for 100 parts by weight, at least 70 parts by weight of the terpolymer (A) and at most 30 parts by weight of at least one copolymer (B) selected from ethylene copolymers comprising of: from 86 to 93 mol% of ethylene; and from 7 to 14 mol% of at least one copolymerisable monomer selected from alkyl (meth)acrylates whose alkyl group has from 1 to 8 carbon atoms; and ethylene copolymers comprising of: 92 to 98 mol% of ethylene; and from 2 to 8 mol% of at least one  $C_3-C_{10}$   $\alpha$ -olefin, the ethylene/ $\alpha$ -olefin copolymers having a density in the range of 0.875 to 0.905, the terpolymer (A) having undergone at least a partial dynamic crosslinking, using a crosslinking agent containing at least one functional group capable of reacting with the anhydride functional group of the terpolymer (A). Also included is a process for the production of the above composition and moulded articles obtained from the composition.

26 OCT 1990

**Intellectual Property Details**

Patent Number	228556
International Application Number	
WO Publication Number	
Patent Type	Patent Convention
Current Status	Granted and Sealed
Patent Title	CROSSLINKED POLYMER COMPOSITIONS, A PROCESS FOR THEIR PRODUCTION AND MOULDED ARTICLES OBTAINED

**Documents**

Abstract/Abridgement	<a href="#">Document</a>
----------------------	--------------------------

**Class**

Classification	Schedule and Edition
IPC C08L23/00	IPC2

**Dates**

Filed Date	31-03-1989
Renewal Date	31-03-2002

**Conventions**

Number	Date	Country
	18-04-1988	France

**Associations**

No associations on record or public access is restricted

**Actions**

Date	Action
26-11-1996	Registered
31-03-1996	Renew
25-03-1996	Renew
31-03-1993	Renew
31-03-1989	Filed

**Applicants & Licensees**

Applicant:	NORSOLOR
Address	Address not held

**Applicant & Licensee History**

No applicants nor licensees on record or public access is restricted

**Inventors**

No inventors on record or public access is restricted

**Address for Service**

No address for service on record or public access is restricted

**Contact**

NORSOLOR

Unknown

---

**Your Selection Criteria**

IPOL Database Search

**Collection:** Public

**Patent Number:** 228556

The information contained in the databases accessible through this site has been taken from files held at the Intellectual Property Office of New Zealand. This site is not intended to be a comprehensive or complete source of intellectual property information. The Intellectual Property Office will not be liable for the provision of any incorrect or incomplete information.

To obtain further assistance on the use of this Internet site please contact [webmaster@companies.govt.nz](mailto:webmaster@companies.govt.nz) or free-phone 0508 266726. Mobile and international callers telephone (03) 962 2602. To obtain information on how to apply for a patent, trade mark or design telephone (04) 560 1600.

Delivered: 04th October 2000 12:26:21